

CASEA Bauprotec SLP – Tanking & Plinth Render

CASEA Bauprotec SLP is a factory produced Lightweight Sand & Cement Render specially designed for hand and machine application produced to EN 998-1:2016. It is manufactured from a controlled blend of selected aggregates, cement, polymers, fibres and other components to give a high quality water repellent rendering product which is suitable for use in external rendering and internal plastering. The unique tanking properties of this render makes it suitable for application on basement walls and plinths.

- Water Repellent
- Lightweight, suitable for thermal insulating blockwork
- Machine or Hand Application
- High Mechanical Stress
- Weather Resistant
- CE Marked
- EN 998-1:2016

Field Of Application

A tanking render for facades and walls constructed out of low, medium, high density blockwork and concrete. Bauprotec SLP is particularly suitable for application onto thermal insulating blockwork such as Poroton blocks.

Substrate

Substrates to be rendered should be examined for contamination, deterioration, surface roughness, suction and strength. Dust and contamination such as residues of concrete release agents, gypsum plaster, paint, other coatings, organic growth, salts and efflorescence should be removed prior to rendering. Salts and efflorescence should be removed by dry brushing (non-metallic bristles). Other special precautions may need to be taken if this removal is not achievable. The line and flatness of the substrate should also be assessed to determine if the render can be applied to a uniform thickness or if dubbing out is required. The substrate should be dry and free of frost, with a temperature of +5 °C or above at the time of rendering. It is important for the wall not to be too wet at the time of rendering. Walls that have recently been exposed to heavy rain should be allowed to dry out sufficiently before rendering is attempted.

Preparation

Bauprotec SLP should only be applied to mature stable surfaces. A minimum of one month should be allowed following completion of the wall construction before application of the render commences. In slow drying situations, a longer interval should be allowed.

All substrates must be clean, sound and dust free as the render relies on a combination of suction and surface texture to achieve bond. The recommendations set out in EN 13914-1:2016 and BS 5262:1991 should be followed. It is essential that all steps are taken to ensure that a satisfactory bond is achieved between the render and the substrate.

Instructions

CASEA Bauprotec SLP can be applied using a suitable spray rendering machine, e.g. G4, G5, m3, S48, MP25 or SP11 and can be transported on all pneumatic conveyor systems. When hand applied, mix for 5 minutes using a suitable electric mixer. In case of great unevenness in the substrate (e.g. rough stone masonry) the recesses require dubbing out. On high absorbent substrates, it is essential to apply the render in two passes, pressing the first pass well into the surface using a straight edge hand trowel. Before the first layer dries, apply the second pass (wet in wet) extending the render to the desired uniform thickness. When the render is partially set, finish to the desired finish using a steel float, wood float or grid float. The open time after mixing is approximately two and a half hours. However, the open time greatly depends on the consistency of the render, the ambient temperature and the absorbency of the substrate. Min thickness 10mm max 20mm per coat application. Do not mix in any other products.

Application

During application the air and substrate temperature must be between 5-35°C. Bead out the application area with Stainless Steel, Aluminium or UPVC beading, which also serves as a reference for the thickness applied. Beads need to be carefully bedded in Bauprotec SLP. Always maintain a wet edge, when working in sections. In sunny weather, work should commence on the shady side of the building and be continued, following the sun to prevent the rendering drying out too rapidly.

Practical Advice

We recommend the use of a mineral key coat on concrete and smooth / non-absorbent substrates prior to the application of Bauprotec SLP. Fibreglass mesh must be embedded into the render when applied on critical substrates, in case of changes in substrate material and at stress points around openings.

CASEA Bauprotec SLP – Tanking & Plinth Render

Storage

9 months under dry, protected conditions.

Disposal Considerations

13.1 Waste treatment methods: Recommendation: Must not be disposed together with household garbage. Do not allow product to reach sewage system. European waste catalogue 17 08 02. Uncleaned packaging: Recommendation: Disposal must be made according to official regulations. Recommended cleansing agents: Water, if necessary together with cleansing agents.

Safety

Classification according to Regulation (EC) No 1272/2008: **GHS05** corrosion, Eye Dam. 1 H318 Causes serious eye damage. **GHS07**, Skin Irrit. 2 H315 Causes skin irritation. Labelling according to Regulation (EC) No 1272/2008. The product is classified and labelled according to the CLP regulation: **Hazard pictograms:** GHS05. **Signal word:** Danger. **Hazard-determining components of labelling:** calcium dihydroxide, Cement, portland, chemicals. All standard precautions for the handling of construction materials/chemicals must be taken. See CASEA Health and Safety Data Sheet for further detailed information.

Hazard Statements

H315 Causes skin irritation.

H318 Causes serious eye damage.

Precautionary Statements

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read carefully and follow all instructions.

P264 Wash thoroughly after handling.

P280 Wear protective gloves/protective clothing/eye protection/face protection/hearing protection.

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310 Immediately call a POISON CENTER/doctor/.


P321 Specific treatment (see on this label).

P332+P313 If skin irritation occurs: Get medical advice/attention.

CASEA Bauprotec SLP – Tanking & Plinth Render

Technical Information

Designation	CS III as per DIN EN 998-1
Delivery	approx 850 l/t approx 55 m ² @ 15mm approx 1.8 m ² per 30kg bag
Water Demand	8 l per 30 kg bag
Compressive Strength	approx 5.0 N/mm ²
Flexural Strength	>2.0 N/mm ²
Modulus Of Elasticity	approx 2.5 kN/ mm ²
Capillary Water Absorption	W2 as per DIN EN998
Water Vapour Permeability Coefficient	$\mu \leq 25$
Adhesion	≥ 0.08 N/mm ² FP A, B or C
Thermal Conductivity (Tabular value)	λ_{10} , dry,mat ≤ 0.39 W/(mK) at P=50% λ_{10} , dry,mat ≤ 0.43 W/(mK) at P=90%
Grain Size	0-1 mm
Reaction To Fire	Building Material class A1, non-combustible

	<p>CASEA GmbH Pontelstraße 3 99755 Ellrich Germany</p>
<p>10 CASEA-114 705 EN 998-1 Lightweight rendering/plastering mortar LW Plastering of ceilings and walls inside and outside of buildings</p>	
Reaction to fire	A1
Compressive strength	CS III
Capillary Water Absorbption	W2
Water Vapour Permeability coefficient	$\mu \leq 25$
Adhesion	≥ 0.08 N/mm ² FP: A, B or C
Thermal Conductivity (Tabulated value)	λ_{10} , dry,mat ≤ 0.39 W/(mK) @ P=50% λ_{10} , dry,mat ≤ 0.43 W/(mK) @ P=90%
Durability	NPD*
Dangerous Substances	NPD*

*NPD = No Performance Determined

CASEA
WORKING FOR THE FUTURE

FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 RO: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie

