

SMET One Coat Projection Plaster HC

SMET One Coat Projection Plaster HC is a factory-produced hard coat One Coat Gypsum Plaster designed for machine application produced to EN 13279-1. It is manufactured from a controlled blend of selected gypsum and other components to give a high quality, high strength plastering product that is suitable for use in internal plastering. The unique properties of this render make it suitable for application on low, medium and high-density blockwork substrates.

Benefits

- One coat machine application
- High strength
- Perfect workability
- Perfect smooth finish in one coat
- High whiteness index
- Sustainable
- Application up to 20mm in one pass
- DIN EN 13279-1, B1

Field Of Application

A One Coat Projection Plaster HC for walls constructed out of low, medium and high-density blockwork and any other masonry substrate. The product's special composition allows the product to be applied in one coat application.

Substrate

Substrates to be plastered should be examined for contamination, deterioration, surface roughness, suction and strength. Dust and contamination such as residues of concrete-release agents, paint, other coatings, organic growth, salts, and efflorescence should be removed prior to plastering. Salts and efflorescence should be removed by dry brushing (non-metallic bristles). Other special precautions may need to be taken if this removal is not achievable. The line and flatness of the substrate should also be assessed to determine if the plaster can be applied to a uniform thickness or if dubbing out is required. Concrete blockwork substrates should have a residual moisture content of <3% and free of frost, with a temperature of +5 °C or above at the time of plastering.

Preparation

SMET One Coat Projection Plaster HC should only be applied to mature stable surfaces. A minimum of one month should be allowed following completion of the wall construction before plaster application commences. In slow drying situations, a longer interval should be allowed. All substrates must be clean, sound and dust free as the plaster relies on a combination of suction and surface

texture to achieve bond. The recommendations set out in EN 13914- 1:2005 and BS 5262:1991 should be followed. It is essential that all steps are taken to ensure that a satisfactory bond is achieved between the render and the substrate.

Instructions

SMET One Coat can be applied using all suitable spray rendering machines (e.g., Ritmo, G4, G5, m3, S48, MP25, SP11) and can be transported on all pneumatic conveyor systems. In case of great unevenness in the substrate (e.g., rough stone masonry) the recesses require dubbing out. On high absorbent or non-absorbent substrates, it is essential to apply primer prior to plastering. When the plaster is partially set, finish to the desired finish using a steel float. The open time, after mixing, is approximately 2 ½ hours. However, the open time greatly depends on the consistency of the plaster, the ambient temperature and the absorbency of the substrate.

Application

During application, the temperature must be between 5 - 35°C. Bead out the application area with stainless steel, aluminium or UPVC beading, which also serves as a reference for the thickness applied. Beads need to be carefully bedded in SMET One Coat Projection Plaster HC. Always maintain a wet edge when working in sections.

Utilising a dehumidifier:

7 days after the application of plaster, it is possible to speed up the drying process by the introduction of heat and using a dehumidifier with correct capacity for the m³ area of the building. Use several dehumidifiers if required. Keep windows and doors closed to allow the dehumidifier to work efficiently.

Practical Advice

We recommend the use of Casuprim HB on concrete and smooth / non-absorbent substrates and Casuprim AS on highly absorbent substrates prior to the application of SMET One Coat Projection Plaster HC. Fibreglass mesh must be embedded into the plaster when applied on critical substrates, in case of changes in substrate material and at stress points around openings. See accompanying datasheet: *SMET One Coat Projection Plaster HC Application Guide*.

Storage

12 months under dry, protected conditions.

Disposal Considerations

Waste treatment methods: Recommendation: Must not be disposed together with household garbage. Do not allow product to reach sewage system. European waste catalogue 17 08 02. Uncleaned packaging: Recommendation: Disposal must be made according to official regulations. Recommended cleansing agents: Water, if necessary together with cleansing agents

Safety

Classification according to Regulation (EC) No 1272/2008: GHS05 corrosion. Eye Dam. 1 H318 Causes serious eye damage. **Hazard pictograms:** GHS05. **Signal word:** Danger. **Hazard-determining components of labelling:** calcium dihydroxide. All standard precautions for the handling of construction materials/chemicals must be taken. See Health and Safety Data Sheet for further detailed information.

Hazard Statements

H318 Causes serious eye damage.

Precautionary Statements

P102 Keep out of reach of children.

P261 Avoid breathing dust/fume/gas/mist/vapours/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.


P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310 Immediately call a POISON CENTER/doctor/.

UFI CODE: Q230-J0HS-V00N-VEPS

Technical Information

Standard	EN 13279-1 B1/50/2
Compressive Strength	≥ 5.0 N/mm ²
Flexural Strength	≥ 1.5 N/mm ²
Minimum Thickness	9mm
Maximum Thickness	20mm
Yield	9.5 kg/m ² per 10mm approx. 2.6 m ² per 25kg bag @ 10mm
Open time	2.5 hours
Shore Hardness C	80
Reaction To Fire	A1
Grain Size	<1.5 mm

	<p>Gypsum Plus, S.L Pol. Ind. 1 Calle A, No. 19 Cintruenigo (Navarra) Spain</p>
	<p>05 EN 13279-1:2008 EN 13279-1 - B1/50/2</p> <p>Plastering of ceilings and walls within buildings</p>
Reaction to fire	A1
Direct airborne sound insulation	NPD
Thermal resistance	NPD
Dangerous substances	NPD

*NPD = No Performance Determined

CASEA
WORKING FOR THE FUTURE

FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 RO: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie

